

TEMPERATURA Y PESOS ESPECIFICOS - TEMPERATURES AND SPECIFIC GRAVITY

Metal	Metal	Punto de fundición Melting point ° C.	Pesos específicos Specific gravity
Cobre	Copper	1083	8.96
Oro	Gold	1063	19.36
18Kt. Verde	18Kt. Green	988	15.90
18Kt. Amarillo	18Kt. Yellow	927	15.58
18Kt. Blanco	18Kt. White	943	14.64
18Kt. Rojo	18Kt. Red	902	15.18
14Kt. Verde	14Kt. Green	963	14.20
14Kt. Amarillo	14Kt. Yellow	879	13.07
14Kt. Blanco	14Kt. White	996	12.61
14Kt. Rojo	14Kt. Red	935	13.26
10Kt. Verde	10Kt. Green	860	11.03
10Kt. Amarillo	10Kt. Yellow	907	11.57
10Kt. Blanco	10Kt. White	1079	11.07
10Kt. Rojo	10Kt. Red	960	11.59
Plomo	Lead	327	11.36
Paladio	Palladium	1555	12.00
Platino	Platinum	1773	21.45
15% Iridio Plat.	15% Iridio Plat.	1821	21.59
10% Iridio Plat.	10% Iridio Plat.	1788	21.54
5% Iridio Plat.	5% Iridio Plat.	1779	21.50
Plata Pura	Pure Silver	961	10.53
Plata de ley	Sterling silver	893	10.40
Estaño	Tin	232	7.30
Zinc	Zinc	419	7.14
Cera	Wax	-	
Latón	Brass		% Cu % Zn 8,96 7,14



HISPANA

de Maquinaria, S.A.

Tel. +34 93 3091707 Fax. + 34 93 3090702

e-mail: hispana@hispanaspain.com

internet: <http://www.hispanaspain.com>

Calle Pallars, 85 - 91 - Barcelona 08018 - España (Spain)